W W W . O I L C E N T E R . C O M

252

LIQUI-LOK

Zinc-Free Thread-Locking Compound

PRODUCT DESCRIPTION

A zinc-free, thread locking compound, 252 LIQUI-LOK is specially formulated to replace the welding of casing joints and threaded connections. This two-part epoxy compound is easily mixed under wide range of temperatures due to its workable consistency. 252 LIQUI-LOK is unaffected by vibration, pounding, or expansion due to temperature changes. It withstands high break-out torque and provides a leakproof seal.

BENEFITS

Zinc-free

GEAR OILS

MOTOR OILS

HYDRAULIC OILS

PIPE COATINGS

THREAD SEALANTS

BEARING GREASES

SPECIALTY

GREASES

THREAD COMPOUNDS

SUCKER ROD

PRESERVATIVES

GREASE SEALS

CLEANERS & **DEGREASERS**

PIPE STORAGE

COMPOUNDS

CORROSION

INHIBITORS

COMPOUNDS

LUBRICANTS &

TOOL JOINT & DRILL COLLAR

COMPOUNDS

SEALANTS

THREAD LOCKING

RUST &

VALVE

COATINGS

OUTSIDE

WIRELINE

- Environmentally friendly in cured form
- Mixes easily
- Workable consistency in excess of one hour
- Water resistant
- Oxidation resistant
- Withstands high break-out torque
- Provides a leakproof seal and strong permanent bond
- Self lubricating
- Unaffected by vibration, pounding or temperature
- Excellent adhesion

APPLICATION

- Thoroughly clean male and female threads to remove all thread dope, oil, and grease.
- Dry threads completely prior to application of 252 Liqui-Lok.
- Thoroughly mix contents of can; add entire bottle of hardener and continue mixing until completely uniform.
- When used in conjunction with float equipment, apply 252 Liqui-Lok to male threads using a putty knife or spatula.
- Make up joints final torque without delay.

NOTE

Setting action begins immediately after addition of the hardener. The mixture will remain in a workable consistency from 45 minutes to 2 hours under average conditions. Curing time may be reduced by elevating the temperature up to 250°F (121°C) or increased by lowering the temperature. The cure seal may be broken out by heating the joint to >450°F (232°C). Wet joints or high moisture conditions may affect curing ability.

TYPICAL OBSERVATIONS 252

Chemical Family	Epoxy Polymer Resin
Color	Gray
Appearance	Paste
ASTM Penetration @ 77°F (25	5°C) 360
Type Curing	Thermo Curing
Density lb/gal	11.51
Specific Gravity @ 25°C	1.38
Flash Point	>400°F (>204°C)
Solubility in Water	Insoluble
Friction Factor	1.3
Shelf Life (unopened container)	Two years

TYPICAL OBSERVATIONS 252 Hardener

Appearance	Liquid
Color	Pale Straw Colored
Odor	Aminic
Density, lb/gal @ 77°F (25°C)	8.51
Specific Gravity	1.02
Solubility in Water	Appreciable (>10°%)
Percent Volatile	Nil
Flash Point	>200°F (>93°C)

COVERAGE CHART

(FOR 1 POUND KIT)

PIPE SIZE	NO. OF JOINTS
4½"	20 Joints
5½"	12 Joints
65/8"-7"	8 Joints
75/8"-95/8"	6 Joints
10¾"–13¾"	4 Joints
16"–20"	2 Joints

(FOR 1/2 POUND KIT)

PIPE SIZE	NO. OF JOINTS
4½"	10 Joints
5½"	6 Joints
65/8"-7"	4 Joints
75/8"-95/8"	3 Joints
10¾"-13¾"	2 Joints
16"-20"	1 Joint

RELATED PRODUCTS

250 Liqui-Lok Thread Locking Compound



Made in U.S.A.

Manufactured by

BALMAR LLC

616 WEST PONT DES MOUTON ROAD | LAFAYETTE, LA 70507

Sales Locations:

LAFAYETTE, LA | HOUSTON, TX | LONGVIEW, TX | MIDLAND, TX | OKLAHOMA CITY, OK current information relating to this product.

*Registered trade name of 03/20/18 Oil Center Research, Inc.

The product information and specifications listed in this publication are constantly being updated to keep up with government regulations and technology changes. Please visit our web site, www.oilcenter.com, or contact your Account Representative for the most

